



**Passary Minerals Ltd.**  
MINES . MINERAL . REFRACTORY

## PRECAST PURGING PLUGS

DESCRIPTION	PAS PREFAB PL1
Base Component	Fused Alumina & Sintered Alumina Grains
<b>Physical Properties</b>	
Refractoriness °C	40+ 1885+
Maximum Service Temperature °C	1825
Dry Density (gm/cc) after drying at 110 °C	2.90 min.
Cold Crushing Strength (Kg/cm <sup>2</sup> ) after heating at 1600 °C / 3 Hrs.	1150 min.
P. L. C % (max) after heating at 1600 °C / 3 Hrs.	± 0.2
<b>Chemical Analysis</b>	
Al <sub>2</sub> O <sub>3</sub> (%) Min	93.00
Fe <sub>2</sub> O <sub>3</sub> (%) Max	0.50